



Accoya® wood

# DATA SHEET

Accoya is a modified wood that sets a new benchmark for wood performance, finish and sustainability. Through extensive testing and use in applications worldwide, it's proven to outperform the competition.

## Key features

Accoya wood is produced from sustainably sourced, fast growing wood and manufactured using Accsys' proprietary patented modification process from surface to core.



HIGHLY STABLE



HIGHLY DURABLE



IDEAL FOR COATING



EXCELLENT MACHINABILITY



BAREFOOT FRIENDLY



NON TOXIC



SUSTAINABLY SOURCED



NATURAL WOOD



100% RECYCLABLE



THERMAL INSULATOR



INSECT RESISTANT



STRUCTURALLY CERTIFIED

Manufactured by:



**STAR MOULDING & TRIM COMPANY**

6606 W 74th St, Bedford Park, IL 60638

708.458.1040

www.starmoulding.com sales@starmoulding.com

## Standard lengths & grades

**94.5", 118.1", 141.7", 165.4", 189"**

Intermediate lengths of 70.9", 106.3", 129.9", 153.5" and 177.2" also available on a lower volume basis. Finger jointed available in 165.4", 189", and 236.2" lengths.

- › All A1, A2 and B grade dimensions are actual rough sawn.
- › Companies processing Accoya can supply a wide range of standard and custom profiles from these sawn sizes.
- › Accoya is available in four primary grades:

**A1:** 4 sides primarily clear.

**FJ:** A1 finger-jointed to clear lengths.

**A2:** 3 sides primarily clear.

**B:** Greater tolerance for defects such as knots, resin pockets, wane, or edge damage.

## Standard dimensions & grades

Thickness	Widths				Grades
	4"	5"	6"	8"	
4/4	✓	✓	✓	✓	A1, A2, B
5/4		✓	✓	✓	A1, A, B
6/4		✓	✓	✓	A1, A2, B
8/4	✓	✓	✓*	✓*	A1, FJ*, A2, B
10/4	✓*	✓*	✓*	✓*	A1, FJ*, A2
12/4	✓*	✓*	✓*	✓*	A1, FJ*, A2

\* See Finger Joint leaflet for actual FJ dimensions

Material
100% Solid Accoya wood
Durability
AWPA E7 & E10, Average rating > 9. Accoya is an effective barrier against a broad spectrum of wood-destroying organisms. Rigorous testing in the lab as well as in prone settings like the Southeast US, Australia, Japan and New Zealand confirm this.
Equilibrium Moisture Content
3–5 % at 65% relative humidity, 20°C
Density
Average 32 pcf at 65% RH, 20°C, Range 27 to 37 pcf
Shrinkage
<b>WET – 65% RH / 20°C*</b> Radial – 0.4% Tangential – 0.8% <small>*Average Values</small>
<b>WET – Oven Dry*</b> Radial – 0.7% Tangential – 1.5%
Fire Rating
Class C in USA (ASTM E84) and D in Europe (EN149915) like most softwoods.
Thermal Conductivity
ASTM C177, $\gamma = 0.102 \text{ W/m}\cdot\text{K}$ EN 12667, $\lambda = 0.12 \text{ W/m}\cdot\text{K}$
Bending Strength
ASTM D143, MOR = 13,144 psi
Bending Stiffness
ASTM D143, MOE = 1,297,492 psi
Janka Hardness
ASTM D143, Side = 922 LBF, End grain = 1484 LBF.
Certification & Approval
ICC ESR 2825: Certified as compliant with US Building Code for decking & porch boards in termite zones; for both Above Ground & Ground Contact applications.  Forest Stewardship Council (FSC) Certified  WDMA I.S. 4-15A: Approved for Hallmark Certification Program Cradle-to-Cradle: GOLD Overall; Platinum in Material Health



## Insect barrier

Accoya wood is indigestible to a wide range of pests and an effective barrier to attack. Five year ground contact testing by independent laboratories in Florida USA, Northern Territory Australia and sites across Thailand has shown less termite damage on Accoya than on naturally durable species such as FEQ Burmese Teak and Spotted Gum.

## Salt water contact and immersion

Accoya is not detrimentally affected by salt water contact or immersion. Field testing over 10 years immersion have shown some attack on Accoya by marine organisms but less than that sustained on other durable woods in test.

## Machinability

Processing does not affect the unique properties of Accoya wood, as it is modified to the core. It is relatively easy to process and comparable to a softwood or medium density hardwood such as Yellow Poplar (Tulip Wood). With the right training no special tools are required for cross cutting, ripping, planing, routing and drilling. Further details can be found in the Accoya Wood Information Guide.

## Gluing

Both load bearing and non-load bearing applications have been tested using adhesive systems for laminating, finger jointing and frame corner joints. While good results can be achieved with most common adhesives, PU, EPI, epoxy and PRF give the best results. Results using polyvinyl acetate (PVAc) can vary greatly. MUF adhesives should be avoided. Contact your adhesive supplier for more information.

## Finishing

A finish or coating does not need to be applied to Accoya to achieve longevity and dimensional stability. Details on natural weathering of uncoated Accoya can be found in the Wood Information Guide. Most commonly used coating systems can be used on Accoya wood. Testing has been performed with a full range of oil-based and water-based coating systems. Leading coating manufacturers have found that their film form coating systems last longer on Accoya. Contact your coating supplier for more information.

## Fastening

The use of corrosion-proof steel fastenings that conform to ASTM A153 is recommended such as 304 & 316 stainless steel. Use of other metals and alloys is included in the Accoya Wood Information Guide.

For more information please refer to the Wood Information Guide at  
[www.accoya.com](http://www.accoya.com)